

NUMERICAL PROCEDURES FOR THE CALCULATIONS OF
INORGANIC SOLUBILITY AND COHESIVE PARAMETERS

DANIEL D. I. AWSON

Jet Propulsion Laborat

The basic equation for the Hildebrand parameter is:

$$\delta = (\Delta H - RT)^{1/2} / V^{1/2} \quad (I)$$

Where ΔH is the change in enthalpy, R is the gas constant, T is the temperature (K), and V is the molar volume. The controlling term is ΔH , which has two (liquid and crystal) states. From the first law of thermodynamics it is evident that heats of vaporization (ΔH_v) and sublimation (ΔH_s) can be calculated for liquid or crystalline phases. The equations are:

$$\Delta H_v^\circ = \Delta H_f^\circ(\text{ideal gas}) - \Delta H_f^\circ(l) \quad (II) \text{ liquid state}$$

$$\Delta H_s^\circ = \Delta H_f^\circ(\text{ideal gas}) - \Delta H_f^\circ(c) \quad (III) \text{ crystalline state}$$

When the reaction or process evolves heat, the sign of the change in enthalpy is negative. Conversely, when the reaction or process absorbs heat, the sign of the change in enthalpy is positive.

Density Data

To prepare tables of the parameters it is required to have density data as a function of temperature. Two types of data are needed: density of solid materials and density of melt phase materials. Toulourian et. al (Ref. 1) have generated large numbers of thermal linear expansion data for solids. These can be used to estimate density by means of: (IV)

$$D_T = \frac{D_0}{1 + (0.03 \Delta \ell / \ell_0)} \quad (IV)$$

Where D_t and D_0 are the densities at temperature T_k and T_0 respectively, and $\Delta\ell/\ell_0$ is the relative change in linear dimension. The reference temperature for ℓ_0 of the solid at a temperature T/K of the solid material is 20°C. It is also necessary to have density data for the same material in the melt phase (Ref. 2).

Table I Calculation of Inorganic Solubility and Cohesive Parameters for Lithium Chloride

LITHIUM CHLORIDE		COHESION PARAMETERS			
	T, K	$V, \text{cm}^3/\text{mol}$	AH, kcal/mole	$\delta, \text{cal}^{1/2}\text{cm}^{-3/2}$	$\delta, \text{MPa}^{1/2}$
SOLID	298	20.52	50.81	49.46	101.17
	300	20.52	50.79	49.46	101.46
	400	20.81	50.42	48.84	99.91
	500	21.11	50.03	48.19	98.58
	600	21.45	49.61	47.51	97.58
	700	21.81	49.12	46.78	95.71
	800	22.07	48.59	46.14	94.39
	883	22.22	48.03	45.64	93.36
	883	28.22	43.37	38.41	78.55
	900	28.37	44.26	38.69	79.15
	1100	30.11	41.99	36.36	74.37
	1200	31.07	41.39	35.43	72.48
	SOLUBILITY PARAMETERS				
LIQUID	298	20.53	46.62	47.34	96.84
	300	20.52	46.61	47.35	96.86
	400	20.81	46.24	46.74	95.61
	500	21.11	45.84	46.09	94.27
	600	21.45	45.36	45.38	92.82
	700	21.81	44.62	44.53	91.88
	800	22.07	43.92	43.79	89.58
	883	26.21	43.71	42.91	78.88
	883	28.21	43.37	38.01	78.66
	900	28.37	43.24	38.23	78.21
	1000	29.21	42.61	37.29	76.27
	1100	30.11	41.92	36.33	74.31
	1200	31.07	41.39	35.43	72.48